

509,530  
(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
9 October 2003 (09.10.2003)

PCT

(10) International Publication Number  
**WO 03/082781 A1**

(51) International Patent Classification<sup>7</sup>: **C07C 2/12**,  
303/06, 309/31, 2/66, 15/107, 29/16

(21) International Application Number: PCT/US03/09733

(22) International Filing Date: 28 March 2003 (28.03.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/368,927 29 March 2002 (29.03.2002) US

(63) Related by continuation (CON) or continuation-in-part (CIP) to earlier applications:

US	60/368,927 (CON)
Filed on	29 March 2002 (29.03.2002)
US	60/369,232 (CON)
Filed on	29 March 2002 (29.03.2002)
US	60/368,928 (CON)
Filed on	29 March 2002 (29.03.2002)
US	60/368,917 (CON)
Filed on	29 March 2002 (29.03.2002)

(71) Applicant (for all designated States except US): **EXXON-MOBIL CHEMICAL PATENTS INC.** [US/US]; 5200 Bayway Drive, Baytown, TX 77520-5200 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **DUNCAN, Carolyn, B.** [US/US]; 7312 N. Jefferson Place Circle, Baton Rouge, LA 70809 (US). **TURNER, David, W.** [US/US]; 4520 S. Sherwood Forest, Suite 104-180, Baton Rouge, LA 70816 (US). **KEENAN, Michael, J.** [US/US]; 17133 Chadsford Avenue, Baton Rouge, LA 70817 (US). **GREEN, Ernest,**

**E.** [US/US]; 11134 N. Lakeside Oaks, Baton Rouge, LA 70810 (US). **SALEH, Ramzi, Y.** [US/US]; 8008 Bluebonnet Road, 16-15, Baton Rouge, LA 70810 (US). **CAERS, Raphael, F.** [BE/BE]; Prins Boudewijnlaan 189, B-2650, Edegem (BE).

(74) Agents: **MORENO, Louis, N.**; ExxonMobil Chemical Company, Law Technology, P.O.Box 2149, Baytown, TX 77522-2149 et al. (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **OLEFIN OLIGOMERIZATION PROCESS**

(57) Abstract: In a process for oligomerizing a C<sub>2</sub> to C<sub>6</sub> n-olefin feedstock over surface deactivated ZSM-23, the feedstock contains from about 0.1 wt% to about 25 wt% of an iso-olefin and the C<sub>12</sub>+ fraction of the oligomerized olefin product contains less than 0.5 atom% of quaternary carbon atoms.

WO 03/082781 A1

## **OLEFIN OLIGOMERIZATION PROCESS**

### **FIELD**

[0001] This invention relates to a process for oligomerizing a lower molecular weight olefin to produce a higher molecular weight olefin mixture, more specifically a substantially linear olefinic hydrocarbon mixture.

### **BACKGROUND**

[0002] Long chain olefins ( $C_{10}+$ ) are important starting materials in the production of sulfonate surfactants, in which the olefins are used to alkylate aromatic hydrocarbons and the resultant alkyl aromatics are sulfonated to produce alkylaryl sulfonates. In addition, the alcohols of long chain olefins have considerable commercial importance in a variety of applications, including detergents, soaps, surfactants, and freeze point depressants in lubricating oils. In such applications, it is important that the olefins employed are substantially free of quaternary carbon atoms because materials containing quaternary carbon atoms are resistant to biodegradation.

[0003] One potential route for the production of long chain olefins is by the oligomerization of lower ( $C_2$  to  $C_6$ ) olefins, typically using an acidic catalyst, such as a zeolite. Thus, for example, it is known from U.S. Patent Nos. 3,960,978, 4,150,062; 4,211,640; 4,227,992; and 4,547,613 to oligomerize lower olefins over ZSM-5.

[0004] U.S. Patent Nos. 4,855,527; 4,870,038 and 5,026,933 describe a process for producing high molecular weight, slightly branched hydrocarbon oligomers from a lower olefin feedstock employing a shape selective crystalline silicate catalyst, ZSM-23, which has been surface deactivated. The resultant oligomer mixture comprises at least 20% by weight of olefins having at least 12 carbon atoms and an average of from 0.8 to 2.0 branches per carbon chain.

[0005] U.S. Patent No. 5,284,989 is directed to a process for producing substantially linear hydrocarbons by oligomerizing a lower olefin at elevated temperature and pressure in the presence of an acidic aluminosilicate zeolite

selected from ZSM-22, ZSM-23 and ZSM-35 which has been surface-deactivated by contacting with oxalic acid.

[0006] In view of the need to avoid the production of quaternary carbon atoms in the resultant olefin oligomers, it is normal to employ oligomerization feeds which consist essentially of n-olefins and which are substantially free of iso-olefins, such as iso-butylene and iso-amylene. This poses a problem in that one source of lower olefins in a modern integrated oil refinery is the unreacted effluent stream from the MTBE (methyl tertiary butyl ether) production unit, which stream inherently contains up to 5wt% of iso-butylene. Thus, existing oligomerization processes either avoid the use of the MTBE effluent feed or else require expensive purification steps to remove the iso-olefins.

[0007] In accordance with the invention, it has now surprisingly been found that, when surface deactivated ZSM-23 is used to oligomerize a lower olefin feed containing significant quantities of iso-olefins, such as the unreacted effluent from an MTBE unit, the C<sub>12</sub>+ product is substantially free of quaternary carbon atoms. Instead, it is found that any quaternary carbon-containing materials are concentrated in the C<sub>8</sub> fraction, which can then be removed for use as a high-octane gasoline product. Although the reason for this desirable result is not fully understood, it is believed that the size of the pores of the ZSM-23 are such that, although iso-butylene can enter the pores to react with, for example, n-butylene, the resultant branched C<sub>8</sub> oligomer is too large to access the pores for further reaction.

### **SUMMARY**

[0008] Accordingly, the invention resides in a first aspect in an olefin oligomerization process comprising:

- (a) contacting a feedstock comprising one or more C<sub>2</sub> to C<sub>6</sub> n-olefins and from about 0.1 wt% to about 25 wt% of an iso-olefin under oligomerization conditions with surface-deactivated ZSM-23 to produce an oligomerized olefin product; and
- (b) separating from said oligomerized olefin product a C<sub>12</sub>+ fraction containing less than 0.5 atom% of quaternary carbon atoms.

- 3 -

[0009] In one embodiment, said feedstock contains about 0.5 wt% to about 5 wt% of said iso-olefin.

[0010] Typically, said iso-olefin is selected from iso-butylene and iso-amylene.

[0011] Conveniently, the n-olefin in the feedstock is selected from propylene, n-butene and mixtures thereof.

[0012] In one embodiment, the feedstock is the unreacted effluent stream from an MTBE unit.

[0013] Conveniently, the feedstock contains less than 100 ppm of dimethyl ether and has a sulfur content of less than 10 ppm.

[0014] Conveniently, the ZSM-23 has been surface deactivated with a sterically hindered nitrogenous base, such as 2,4,6-collidine.

[0015] In a second aspect, the invention resides in a process for producing a long chain alcohol mixture comprising contacting said C<sub>12</sub>+ fraction with carbon monoxide and hydrogen under hydroformylation conditions and in the presence of a hydroformylation catalyst.

[0016] In a third aspect, the invention resides in a process for producing an alkylaromatic compound comprising contacting an aromatic compound with said C<sub>12</sub>+ fraction under alkylation conditions and in the presence of an alkylation catalyst.

[0017] In a fourth aspect, the invention resides in a process for preparing an alkylaryl sulfonate by sulfonating the alkylaromatic compound produced in accordance with said third aspect of the invention.

### **DETAILED DESCRIPTION OF THE EMBODIMENTS**

[0018] The present invention provides an improved process for producing slightly branched, high molecular weight olefinic hydrocarbons by oligomerizing a lower olefinic hydrocarbon feedstock in the presence of a surface-deactivated ZSM-23 catalyst. The use of such a catalyst is found, unexpectedly, to allow the

use of an olefin feedstock that contains significant quantities of iso-olefins, such as isobutylene, without producing deleterious quantities of quaternary carbon atoms in the C<sub>12</sub>+ fraction.

[0019] The olefinic hydrocarbon feedstock used in the process of the invention comprises one or more C<sub>2</sub> to C<sub>6</sub> n-olefins, such as propene and/or n-butene. In addition, the feedstock contains about 0.1% to about 25%, such as about 0.5% to 5%, of an iso-olefin by weight of the total feedstock. Typically, the iso-olefin will be iso-butylene and/or iso-amylene. One preferred olefinic feedstock for use in the process of the invention is the unreacted effluent stream from an MTBE production unit, which stream typically contains n-butene together with iso-butylene in amounts up to 5 wt%. A practical feedstock, such as an MTBE effluent, may also contain dimethyl ether and sulfur impurities. If present, the dimethyl ether content is preferably less than 100 ppm and the sulfur content is preferably less than 10 ppm.

[0020] The olefinic hydrocarbon feedstock can also contain low molecular weight, typically C<sub>4</sub>-C<sub>6</sub>, saturated hydrocarbons, typically in amounts between about 5% and about 70% by weight of the overall feedstock.

[0021] The oligomerization catalyst used in the process of the invention comprises ZSM-23 which has been surface deactivated, typically by treatment with a sterically hindered nitrogenous base, such as a trialkyl pyridine compound, and preferably with 2,4,6-collidine (2,4,6-trimethyl pyridine, gamma-collidine). The surface deactivating compound should have a minimum cross-sectional diameter greater than the effective pore size of the zeolite to be treated; i.e., greater than 5 Angstroms. ZSM-23 and its characteristic X-ray diffraction pattern are described in detail in U.S. Patent No. 4,076,842, the entire contents of which are incorporated herein by reference. Preferably, the ZSM-23 employed in the catalyst has an alpha value of about 25 and a crystal size of less than 0.1 micron and is conveniently composited with a binder, such as alumina.

[0022] Suitable oligomerization conditions include a temperature of about 160°C to about 250°C, such as about 190°C to about 230°C, for example about 210°C to about 220°C; a pressure in the range of about 500 psig (3447 kPa (gauge)) to about 1500 psig (10342 kPa (gauge)), such as in the range of about

- 5 -

750 psig (5171 kPa (gauge)) to about 1250 psig (8618 kPa (gauge)), and a feed weight hour space velocity (WHSV) in the range of about  $0.1 \text{ hr}^{-1}$  to about  $4.0 \text{ hr}^{-1}$ , such as in the range of about  $0.2 \text{ hr}^{-1}$  to about  $3.0 \text{ hr}^{-1}$ , for example in the range of about  $1.75 \text{ hr}^{-1}$  to about  $2.25 \text{ hr}^{-1}$ .

[0023] Where surface deactivation is achieved by treatment with a trialkyl pyridine compound, the feed to the oligomerization process can include additional trialkyl pyridine compound so that the surface properties of the zeolite are maintained during the process. Further details of the oligomerization process can be found in U.S. Patent No. 5,026,933, the entire contents of which are incorporated herein by reference.

[0024] The product of the oligomerization process of the invention is an olefinic hydrocarbon mixture which comprises at least 5 wt%, such as at least 20 wt%, for example at least 85 wt% of mono-olefin oligomers of the empirical formula:



wherein  $n$  is greater than or equal to 6 and wherein said mono-olefin oligomers comprise at least 20 wt%, and conveniently at least 60 wt%, of olefins having at least 12 carbon atoms and said olefins having at least 12 carbon atoms ( $\text{C}_{12}+$  olefins) have an average of from about 0.8 to about 2.0, such as from about 0.8 to about 1.3,  $\text{C}_1$ - $\text{C}_3$  alkyl branches per carbon chain. Conveniently, the olefins having at least 12 carbon atoms contain no branches other than methyl and ethyl groups.

[0025] In particular it is found that, despite the presence of iso-olefins in the oligomerization feed, the  $\text{C}_{12}+$  olefinic product of the present process contains less than 0.5 atom%, of quaternary carbon atoms. As previously stated, although the reasons for the low quaternary carbon content of the  $\text{C}_{12}+$  olefinic product are not fully understood, it is believed that the size of the pores of the ZSM-23 are such that, although iso-butylene can enter the pores to react with, for example,  $n$ -butylene, the resultant branched  $\text{C}_8$  oligomer is too large to access the pores for further reaction. Thus the iso-olefin reaction products are concentrated in the  $\text{C}_{12}$ -fraction of the oligomerization product and, in the case of a  $\text{C}_4$  olefin feed, in the  $\text{C}_8$  fraction. Because such a fraction inherently has a high octane value, it is

advantageous to remove this fraction from the oligomerization product for use as a gasoline blending component.

[0026] The percentage of quaternary carbon atoms in the the C<sub>12</sub>+ olefinic product is conveniently determined by the <sup>13</sup>C-NMR technique described in U.S. Patent No. 5,849,960 at column 4, line 23 to column 5, line 3 and in particular the J-Modulated Spin Echo NMR technique (JMSE) using a 1/2J delay of 4 ms and incorporating the DEPT-135 NMR correction. The entire contents of U.S. Patent No. 5,849,960 are incorporated herein by reference.

[0027] The lightly branched C<sub>12</sub>+ olefinic hydrocarbon fraction from the oligomerization process of the invention is conveniently used in the production of long chain alcohols for application as, for example, detergents, soaps, surfactants, and freeze point depressants in lubricating oils. Typically this is achieved by hydroformylation, that is reaction with carbon monoxide and hydrogen, according to the Oxo process. Catalysts employed can be cobalt or rhodium which may be modified with phosphine, phosphite, arsine or pyridine ligands, as described in U.S. Pat. Nos. 3,231,621; 3,239,566; 3,239,569; 3,239,570; 3,239,571; 3,420,898; 3,440,291; 3,448,158; 3,448,157; 3,496,203; and 3,496,204; 3,501,515; and 3,527,818, the disclosures of which are incorporated herein by reference.

[0028] Typical hydroformylation reaction conditions include a temperature of about 125°C to about 200°C, a pressure of about 2170 kPa to about 32550 kPa (300 psig to 4000 psig) and a catalyst to olefin ratio of about 1:5000 to about 1:1. The molar ratio of hydrogen to carbon monoxide is usually about 0.5 to about 10, such as about 1 to about 2. The hydroformylation reaction typically produces an aldehyde which can then be hydrogenated to generate the required alcohol product.

[0029] The hydroformylation process can be carried out in the presence of an inert solvent, such as a ketone, e.g., acetone, methyl ethyl ketone, methyl isobutyl ketone, acetophenone, and cyclohexanone; an aromatic compound, e.g., benzene, toluene and the xylenes; a halogenated aromatic compound, e.g., chlorobenzene and orthodichlorobenzene; a halogenated paraffinic hydrocarbon, e.g., methylene chloride and carbon tetrachloride; a paraffin, e.g., hexane,

heptane, methylcyclohexane and isooctane, and a nitrile, e.g., such as benzonitrile and acetonitrile.

[0030] The catalyst ligand may be made of tertiary organo phosphines, such as trialkyl phosphines, triamyl phosphine, trihexyl phosphine, dimethyl ethyl phosphine, diamylethyl phosphine, tricyclopentyl (or hexyl) phosphine, diphenyl butyl phosphine, diphenyl benzyl phosphine, triethoxy phosphine, butyl diethoxy phosphine, triphenyl phosphine, dimethyl phenyl phosphine, methyl diphenyl phosphine, dimethyl propyl phosphine, the tritolyl phosphines and the corresponding arsines and stibines. Included as bidentate-type ligands are tetramethyl diphosphinoethane, tetramethyl diphosphinopropane, tetraethyl diphosphinoethane, tetrabutyl diphosphinoethane, dimethyl diethyl diphosphinoethane, tetraphenyl diphosphinoethane, tetraeperfluorophenyl diphosphinoethane, tetraphenyl diphosphinopropane, tetraphenyl diphosphinobutane, dimethyl diphenyl diphosphinoethane, diethyl diphenyl diphosphinopropane and tetratolyl diphosphinoethane.

[0031] Examples of other suitable ligands are the phosphabicyclohydrocarbons, such as 9-hydrocarbyl-9-phosphabicyclononane in which the smallest P-containing ring contains at least 5 carbon atoms. Some examples include 9-aryl-9-phosphabicyclo[4.2.1]nonane, (di)alkyl-9-aryl-9-phosphabicyclo[4.2.1]nonane, 9-alkyl-9-phosphabicyclo[4.2.1]nonane, 9-cycloalkyl-9-phosphabicyclo [4.2.1] nonane, 9-cycloalkenyl-9-phosphabicyclo[4.2.1]nonane, and their [3.3.1] and [3.2.1] counterparts, as well as their triene counterparts.

[0032] Alternatively, the lightly branched  $C_{12}+$  olefinic hydrocarbon fraction from the oligomerization process of the invention can be used, either alone or in admixture with linear alpha-olefins, as an alkylating agent in a process for the selective alkylation of an aromatic compound (e.g., benzene) with a relatively long chain length alkylating agent to produce substantially linear phenylalkanes. The alkylation process is conducted such that the organic reactants, i.e., the aromatic compound and the olefinic hydrocarbon mixture, are contacted under effective alkylation conditions with a suitable acid catalyst.



Suitable aromatic hydrocarbons include benzene, toluene, xylene and naphthalene, with preferred compounds being benzene and toluene.

[0033] In one embodiment, the catalyst is a homogeneous acid catalyst such as a Lewis acid catalyst, for example aluminum chloride. Alternatively, the homogeneous acid catalyst is a Brønsted acid catalyst, such as HF or phosphoric acid. Suitable alkylation conditions with a homogeneous catalyst include a temperature of from about  $-10^{\circ}\text{C}$  to about  $100^{\circ}\text{C}$ , a pressure of from about 100 kPa to about 2500 kPa (1.0 to 25 atmospheres), a feed weight hourly space velocity (WHSV) of from about  $0.2\text{ hr}^{-1}$  to about  $10\text{ hr}^{-1}$  and an aromatic compound to olefinic hydrocarbon mixture mole ratio of from about 1:1 to about 15:1. Typical reaction conditions include a temperature of from about  $0^{\circ}\text{C}$  to about  $50^{\circ}\text{C}$ , a pressure of from about 100 kPa to about 300 kPa (1.0 to about 3.0 atmospheres), a feed weight hourly space velocity (WHSV) of from about  $0.1\text{ hr}^{-1}$  to about  $0.5\text{ hr}^{-1}$  and an aromatic compound to olefinic hydrocarbon mixture mole ratio of from about 5:1 to about 10:1. The reactants can be in either the vapor phase or the liquid phase and can be neat, i.e., free from intentional admixture or dilution with other material, or they can be brought into contact with the catalyst composition with the aid of carrier gases or diluents such as, for example, hydrogen or nitrogen.

[0034] In a further embodiment, the alkylation process is conducted in the presence of a heterogeneous catalyst, such as a molecular sieve. Suitable molecular sieves include mordenite, particularly dealuminized mordenite and other 6-7 Angstrom pore molecular sieves disclosed in U.S. Patent No. 5,026,933, the entire contents of which are incorporated herein by reference.

[0035] In one practical embodiment, the alkylation catalyst comprises a molecular sieve having an X-ray diffraction pattern including d-spacing maxima at  $12.4\pm 0.25$ ,  $6.9\pm 0.15$ ,  $3.57\pm 0.07$  and  $3.42\pm 0.07$  Angstroms. The X-ray diffraction data used to characterize said molecular sieve are obtained by standard techniques using the K-alpha doublet of copper as the incident radiation and a diffractometer equipped with a scintillation counter and associated computer as the collection system. Materials having the required X-ray diffraction lines are sometimes referred to as molecular sieves of the MCM-22 family and include

MCM-22 (described in U.S. Patent No. 4,954,325), PSH-3 (described in U.S. Patent No. 4,439,409), SSZ-25 (described in U.S. Patent No. 4,826,667), ERB-1 is described in European Patent No. 0293032, ITQ-1 is described in U.S. Patent No. 6,077,498, ITQ-2 is described in International Patent Publication No. WO97/17290, MCM-36 (described in U.S. Patent No. 5,250,277), MCM-49 (described in U.S. Patent No. 5,236,575) and MCM-56 (described in U.S. Patent No. 5,362,697). The entire contents of said patents are incorporated herein by reference.

[0036] The molecular sieve alkylation catalyst can be combined in conventional manner with an oxide binder, such as alumina, such that the final alkylation catalyst contains between about 2 and about 80 wt% sieve.

[0037] With a molecular sieve catalyst, suitable alkylation conditions include a temperature of from about 0°C to about 500°C, a pressure of from about 20 kPa to about 25000 kPa (0.2 to 250 atmospheres), a feed weight hourly space velocity (WHSV) of from about 0.1 hr<sup>-1</sup> to about 500 hr<sup>-1</sup>, and an aromatic compound to olefinic hydrocarbon mixture mole ratio of from about 1:1 to about 20:1. The WHSV is based upon the weight of the catalyst composition employed, i.e., the total weight of active catalyst (and binder if present). Typical reaction conditions include a temperature within the range of from about 100°C to about 350°C, a pressure of from about 100 kPa to about 2500 kPa (1 to 25 atmospheres), a WHSV of from about 0.5 hr<sup>-1</sup> to about 100 hr<sup>-1</sup> and an aromatic compound to olefinic hydrocarbon mixture mole ratio of from about 4:1 to about 15:1. Again, the reactants can be in either the vapor phase or the liquid phase and can be neat, i.e., free from intentional admixture or dilution with other material, or they can be brought into contact with the zeolite catalyst composition with the aid of carrier gases or diluents such as, for example, hydrogen or nitrogen.

[0038] The alkylation process of the invention produces an alkylaromatic hydrocarbon mixture in which the alkyl side chains are lightly branched and have less than 0.5 atom% of quaternary carbon atoms and in which most of the aromatic species are located at the 2- or 3- position in the alkyl side chain. The alkylaromatic hydrocarbon mixture is therefore particularly useful as an intermediate in the production of alkylarylsulfonates, which are useful as detergents or surfactants. Processes for sulfonating alkylbenzenes are described in

- 10 -

the U.S. Patent No. 4,298,547, the entire contents of which are incorporated herein by reference. More particularly, alkylaromatic hydrocarbons may be converted to alkylarylsulfonates by sulfonation of the aromatic ring with sulfuric acid. The sulfonation reaction is well known in the art and is commonly carried out by contacting the organic compound with sulfuric acid at temperatures of from about -70°C to about +60°C. Detailed descriptions of specific commercial processes abound in the literature. See, for instance, pages 60-62 of INDUSTRIAL CHEMICALS, Third Edition, by W. L. Faith et al, published by John Wiley & Sons, Inc.

**CLAIMS**

1. An olefin oligomerization process comprising:
  - (a) contacting a feedstock comprising one or more C<sub>2</sub> to C<sub>6</sub> n-olefins and from about 0.1 wt% to about 25 wt% of an iso-olefin under oligomerization conditions with surface-deactivated ZSM-23 to produce an oligomerized olefin product; and
  - (b) separating from said oligomerized olefin product a C<sub>12</sub>+ fraction containing less than 0.5 atom% of quaternary carbon atoms.
2. The process according to claim 1, wherein said feedstock contains about 0.5 wt% to about 5 wt% of an iso-olefin.
3. The process according to claim 1 or claim 2, wherein said iso-olefin is isobutylene and/or iso-amylene.
4. The process according to any preceding claim, wherein said one or more n-olefins in the feedstock are selected from propylene, n-butene and mixtures thereof.
5. The process according to any preceding claim, wherein said feedstock is the unreacted effluent stream from an MTBE unit.
6. The process according to any preceding claim, wherein said feedstock contains less than 100 ppm of dimethyl ether.
7. The process according to any preceding claim, wherein said feedstock has a sulfur content of less than 10 ppm.
8. The process according to any preceding claim, wherein said ZSM-23 has been surface deactivated with a sterically hindered nitrogenous base.

- 12 -

9. The process according to Claim 8, wherein said sterically hindered nitrogenous base is 2,4,6-collidine.
10. The process according to any preceding claim, wherein said oligomerization conditions include a temperature of about 160 to about 250°C.
11. The process according to any preceding claim, wherein said oligomerization conditions include a temperature of about 190 to about 230°C.
12. The process according to any preceding claim, wherein said oligomerization conditions include a temperature of about 210 to about 220°C.
13. The process according to any preceding claim, wherein said oligomerization conditions comprise a pressure in the range of from about 500 psig (3447 kPa (gauge)) to about 1500 psig (10342 kPa (gauge)).
14. The process according to any preceding claim, wherein said oligomerization conditions comprise a pressure in the range of from about 750 psig (5171 kPa (gauge)) to about 1250 psig (8618 kPa (gauge)).
15. The process according to any preceding claim, wherein said oligomerization conditions comprise a weight hourly space velocity of from about 0.1 hr<sup>-1</sup> to about 4.0 hr<sup>-1</sup>.
16. The process according to any preceding claim, wherein said oligomerization conditions comprise a weight hourly space velocity of from about 0.2 hr<sup>-1</sup> to about 3.0 hr<sup>-1</sup>.

- 13 -

17. The process according to any preceding claim, wherein said oligomerization conditions comprise a weight hourly space velocity of from about  $1.75 \text{ hr}^{-1}$  to about  $2.25 \text{ hr}^{-1}$ .
18. The process according to any preceding claim, wherein said  $\text{C}_{12}+$  fraction has an average of from about 0.8 to about 2.0  $\text{C}_1\text{-C}_3$  alkyl branches per carbon chain.
19. The process according to any preceding claim, wherein said  $\text{C}_{12}+$  fraction has an average of from about 0.8 to about 1.3  $\text{C}_1\text{-C}_3$  alkyl branches per carbon chain.
20. A method for producing a long chain alcohol mixture comprising contacting the  $\text{C}_{12}+$  fraction produced by the process of any preceding claim with carbon monoxide and hydrogen under hydroformylation conditions and in the presence of a hydroformylation catalyst.
21. A method for producing an alkylaromatic compound comprising contacting an aromatic compound with the  $\text{C}_{12}+$  fraction produced by the process of any one of claims 1 to 19 under alkylation conditions and in the presence of an alkylation catalyst.
22. A method for preparing an alkylaryl sulfonate by sulfonating the alkylaromatic compound produced by the method of Claim 21.

## INTERNATIONAL SEARCH REPORT

Intern Application No  
PCT/us /09733

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C07C2/12 C07C303/06 C07C309/31 C07C2/66 C07C15/107  
C07C29/16

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, INSPEC

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 026 933 A (BLAIN DAVID A ET AL) 25 June 1991 (1991-06-25) cited in the application column 2, line 25 - line 38	1-19, 21, 22
Y	column 2, line 65 - column 3, line 10 column 4, line 1 - line 30 column 5, line 25 - column 6, line 13 column 7, line 8 - column 10, line 10; claims; examples II, III, VII-XVIII ---	20
X	US 4 855 527 A (YOUNG LEWIS B ET AL) 8 August 1989 (1989-08-08) cited in the application claims; examples II-III, VII-VIII --- -/--	1-19, 21, 22

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&amp;\* document member of the same patent family

Date of the actual completion of the international search

16 July 2003

Date of mailing of the international search report

28/07/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Seelmann, M

## INTERNATIONAL SEARCH REPORT

Internal Application No

PCT/US /09733

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 284 989 A (APELIAN MINAS R ET AL) 8 February 1994 (1994-02-08) cited in the application column 10, line 3 - line 31 column 11, line 25 -column 13, line 30 claims; examples 1,4,5 ---	1-19,21, 22
Y	US 3 440 291 A (WINKLE JOHN L VAN ET AL) 22 April 1969 (1969-04-22) claims; examples ---	20
A	FR 2 527 201 A (SNAM PROGETTI) 25 November 1983 (1983-11-25) fraction related to line 9 table 2 ---	1-19
A	G. MARCEGLIA ET AL.: "Skeletal isomerization of linear olefins. Isobutene via MTBE cracking butene-1 production etherification or alternative raw materials" CHEMICAL ECONOMY AND ENGINEERING REVIEW, vol. 14, no. 6, 1982, pages 35-40, XP009013980 page 39; tables 3,4 -----	1-19



## INTERNATIONAL SEARCH REPORT

Intern Application No  
PCT/US /09733

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5026933	A	25-06-1991	AU 2215288 A	13-04-1989
			CA 1304420 C	30-06-1992
			DE 3871318 D1	25-06-1992
			EP 0311310 A1	12-04-1989
			JP 1132534 A	25-05-1989
			JP 2562187 B2	11-12-1996
			US 4870038 A	26-09-1989
			US 4855527 A	08-08-1989
US 4855527	A	08-08-1989	AU 2215288 A	13-04-1989
			CA 1304420 C	30-06-1992
			DE 3871318 D1	25-06-1992
			EP 0311310 A1	12-04-1989
			JP 1132534 A	25-05-1989
			JP 2562187 B2	11-12-1996
			US 4870038 A	26-09-1989
			US 5026933 A	25-06-1991
US 5284989	A	08-02-1994	AU 667609 B2	28-03-1996
			AU 5549994 A	24-05-1994
			CA 2141568 A1	11-05-1994
			DE 69322878 D1	11-02-1999
			DE 69322878 T2	27-05-1999
			EP 0667839 A1	23-08-1995
			ES 2127372 T3	16-04-1999
			JP 8502959 T	02-04-1996
			JP 3395137 B2	07-04-2003
			SG 66220 A1	20-07-1999
			WO 9410108 A1	11-05-1994
US 3440291	A	22-04-1969	US 3400163 A	03-09-1968
			BE 678614 A	29-09-1966
			DE 1543471 A1	21-08-1969
			DE 1667286 A1	19-05-1971
			FR 1472711 A	10-03-1967
			GB 1109787 A	18-04-1968
			NL 6604094 A ,B	30-09-1966
			NL 7312880 A ,B,	26-11-1973
			SE 356692 B	04-06-1973
			SE 345254 B	23-05-1972
			US 3420898 A	07-01-1969
			US 3496203 A	17-02-1970
			US 3496204 A	17-02-1970
			US 3501515 A	17-03-1970
			US 3502730 A	24-03-1970
FR 2527201	A	25-11-1983	IT 1151182 B	17-12-1986
			AU 552855 B2	26-06-1986
			AU 1426183 A	24-11-1983
			BE 896789 A1	21-11-1983
			BG 37677 A3	16-07-1985
			BR 8302432 A	17-01-1984
			CA 1218386 A1	24-02-1987
			CH 656119 A5	13-06-1986
			CS 236879 B2	15-05-1985
			DD 209804 A5	23-05-1984
			DE 3318300 A1	24-11-1983
			DK 221583 A	21-11-1983

## INTERNATIONAL SEARCH REPORT

Intern: application No  
PCT/US /09733

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2527201	A	EG 16041 A	30-04-1987
		ES 8500203 A1	01-01-1985
		FR 2527201 A1	25-11-1983
		GB 2121791 A ,B	04-01-1984
		GR 77461 A1	24-09-1984
		IN 159787 A1	06-06-1987
		JP 58219127 A	20-12-1983
		KR 8601850 B1	24-10-1986
		LU 84806 A1	07-03-1984
		MW 1983 A1	13-02-1985
		NL 8301820 A	16-12-1983
		NO 831758 A	21-11-1983
		NZ 204126 A	30-04-1985
		PH 19313 A	14-03-1986
		PL 242092 A1	02-07-1984
		PT 76729 A ,B	01-06-1983
		SE 8302771 A	21-11-1983
		TR 21660 A	17-01-1985
		US 4513153 A	23-04-1985
		YU 110183 A1	28-02-1986
		ZA 8303158 A	25-04-1984
		ZW 10383 A1	10-08-1983

---